

Applicant : Andreas Muth
Appln. No. : 11/539,152
Page : 2

In the Claims:

This listing of claims will replace all prior versions and listings of claims in the application:

1-19. (canceled)

20. (previously presented) A device for producing insulation elements made of mineral wool containing a curable binder from insulation material having a rectangular cross section, comprising:

a conveyor configured to having the insulation material deposited thereon prior to curing; and

a curing oven configured to have the insulation material transported thereto via the conveyor, the curing oven having a molding device therein;

the molding device reducing a cross section of a gap through which the insulation material is transported within the curing oven and compacting the insulation material as it passes therethrough; and

the molding device being configured to provide at least one permanent impression and/or at least one deformation in the insulation material.

21. (previously presented) The device of claim 20, wherein:
the curing oven comprises a tunnel furnace.

22. (previously presented) The device of claim 20, wherein:
the molding device is integrated in a conveyor unit within the curing oven, the conveyor unit comprising at least one first molding element to form the at least one permanent impression and/or at least one deformation, during which process, as a result of contact with a molding surface of the at least one first molding element, the insulation material to be molded assumes a cross-sectional profile that deviates from the rectangular cross section of the insulation material entering the molding device.

Applicant : Andreas Muth
Appln. No. : 11/539,152
Page : 3

23. (previously presented) The device of claim 22, wherein:
the at least one first molding element is configured to contact the insulation material with a pressure contact.
24. (previously presented) The device of claim 22, wherein:
the molding device has at least one second molding element opposite the at least one first molding element.
25. (previously presented) The device of claim 22 wherein:
the at least one molding element comprises at least two molding elements.
26. (previously presented) The device of claim 22, wherein:
the molding device further includes at least one lateral molding element.
27. (previously presented) The device of claim 22, wherein:
the first molding element is formed by a compacting and guiding unit, which, together with the conveyor unit, compacts the insulation material or transports it at an upper side.
28. (previously presented) The device of claim 27, wherein:
the compacting and guiding unit comprises a flight belt.
29. (previously presented) The device of claim 24, wherein:
the first molding element and/or the second molding element are engineered as attachable elements for the conveyor unit or a compacting and guiding unit, which, together with the conveyor unit, compacts the insulation material or transports it at an upper side.
30. (previously presented) The device of claim 29, wherein:
the attachable elements and the conveyor unit are engineered as metal components that have the form of gratings or are provided with ventilation channels.

Applicant : Andreas Muth
Appln. No. : 11/539,152
Page : 4

31. (previously presented) The device of claim 30, wherein:
the components are made of heat-resistant materials.
32. (previously presented) The device of claim 30, wherein:
the components are segmented.
33. (previously presented) The device of claim 29, wherein:
the attachable elements for attachment to the conveyor and/or compacting and guiding unit have quick-release closures.
34. (previously presented) The device of claim 24, wherein:
the first and/or second molding element is arranged such that with respect to a conveying plane of the conveyor unit, its molding surface is inclined about a longitudinal transport axis.
35. (previously presented) The device of claim 20, wherein:
the molding element of the molding device is engineered as an endless loop.
36. (previously presented) The device of claim 35, wherein:
the endless loop includes a plurality of successive segments.
37. (previously presented) The device of claim 20, wherein:
the molding element is engineered such that a differing degree of compaction is obtained over a breadth of the molding surface.
38. (previously presented) The device of claim 20, wherein:
the molding element has a contoured molding surface.

Applicant : Andreas Muth
Appln. No. : 11/539,152
Page : 5

39. (previously presented) The device of claim 38, wherein:
the contoured molding surface comprises an inclined planar surface.
40. (previously presented) The device of claim 38, wherein:
the contoured molding surface comprises grooves and/or projections.
41. (previously presented) A method of producing insulation elements made of mineral wool containing curable binder, comprising:
depositing insulation material on a conveyor;
curing and transporting the insulation material through a curing oven;
subjecting sections of the insulation material to controlled compaction in such a manner that at least one permanent impression and/or deformation is produced in the insulation blanket while the insulation material is curing during its passage through the curing oven.
42. (previously presented) The method of claim 41, wherein:
the curing oven comprises a tunnel furnace.
43. (previously presented) The method of claim 41, wherein:
the mineral wool is rock wool.
44. (previously presented) The method of claim 41, wherein:
the mineral wool is glass wool.
45. (previously presented) The method of claim 41, further including:
providing the insulation material with a non-rectangular cross-sectional profile before or during curing.
46. (previously presented) The method of claim 45, wherein:
the cross-sectional profile comprises at least one depression or projection.

Applicant : Andreas Muth
Appln. No. : 11/539,152
Page : 6

47. (previously presented) The method of claim 46, wherein:
the cross-sectional profile of the insulation element displays two parallel recesses in one surface.

48. (previously presented) The method of claim 41, wherein:
during the step of subjecting sections of the insulation material to controlled compaction, the insulation material is compacted to varying degrees, whereby a density within the insulation elements varies accordingly.

49-52. (canceled)